

# TECHNICAL DATA SHEET



<b>CAS NUMBER</b>	: 68476-25-5
<b>EINECS NUMBER</b>	: 2706667
<b>MATERIAL CODE</b>	: S.PR.C30 (KS.91.M.0100)
<b>PRODUCTION PLANT</b>	: Kaltun - Cine / AYDIN/ TURKIYE
<b>SHORT DESCRIPTION OF MATERIAL</b>	: <b>COATTUN S.PR.C30</b> is a high quality Sodium Feldspar, produced from deposits in the Cine-Milas region, Turkiye

## PHYSICAL & CHEMICAL PROPERTIES OF MATERIAL:

	Particle Size Distribution					Colour			Others				
	Sieve Residue	Malvern (Mastersizer 2000)				Elrepho 450 TS			Density	Bulk Density	Hardness	Humidity	Oil Absorb
	> 0,15mm	D/10	D/50	D/97	D/100	L*	a*	b*	g/cm <sup>3</sup>	g/cm <sup>3</sup>	mohs	%	g/100g
<b>Typ.</b>	<b>0,0 %</b>	<b>3,6µm</b>	<b>30,0µm</b>	<b>100,0µm</b>	<b>160,0µm</b>	<b>96,5</b>	<b>0,15</b>	<b>1,75</b>	<b>2,60</b>	<b>1,04</b>	<b>6</b>	<b>0,2</b>	<b>25</b>
<b>Min.</b>	-	-	<b>26,0µm</b>	-	-	<b>95,5</b>	-	-	-	-	-	-	-
<b>Max.</b>	<b>0,1 %</b>	-	<b>34,0µm</b>	-	<b>180,0µm</b>	-	<b>0,25</b>	<b>2,20</b>	-	-	-	<b>0,5</b>	-

	Chemical Analysis (*)										
	SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	CaO	MgO	Na <sub>2</sub> O	K <sub>2</sub> O	P <sub>2</sub> O <sub>5</sub>	L.O.I	
<b>Typ.</b>	<b>69,23</b>	<b>19,00</b>	<b>0,01</b>	<b>0,02</b>	<b>0,42</b>	<b>0,07</b>	<b>11,00</b>	<b>0,10</b>	<b>0,00</b>	<b>0,15</b>	

(\*) WITH XRF SPECTROMETER

The above figures are typical, average values derived from numerous measurements. This is not a specification



Aydin- Mugla Karayolu 35. Km. 09500 Cine/Aydin-TURKIYE

Phone : +90 256 729 16 00

Fax : +90 256 729 16 15

Web : <http://www.kaltun.com>

e-mail : [kaltun@kaltun.com.tr](mailto:kaltun@kaltun.com.tr)

Doc.No : Coat005  
Issued Date : 13.05.2014  
Revision : 3