

TECHNICAL DATA SHEET

ceratun
S.SAB.673

CAS NUMBER : 68476-25-5
EINECS NUMBER : 2706667
MATERIAL CODE : S.SAB.673 (KS.14.B.0005)
PRODUCTION PLANT : Kaltun - Cine / AYDIN/ TURKIYE
SHORT DESCRIPTION OF MATERIAL : **CERATUN S.SAB.673** is a high quality Sodium Feldspar, produced from deposits in the Cine-Milas region, Turkiye.

PHYSICAL & CHEMICAL PROPERTIES OF MATERIAL:

	Particle Size Distribution				Others			
	Sieve Residue %				Humidity * %		Hardness	Density
	+10mm	+5mm	+0,5mm	-0,5mm	Summer	Winter	Mohs	g/cm ³
Typ.	0,0	5,0	45,0	55,0	3,0	5,0	6	2,60
Min.	-	-	-	45,0	-	-	-	-
Max.	1,0	-	-	-	5,0	7,0	-	-

* Summer season conditions are valid from the beginning of May till the end of September.

	Chemical Analysis **									
	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	L.O.I
Typ.	66,85	17,15	0,17	0,32	0,87	2,25	9,20	0,38	0,31	2,50
Min.	-	16,15	-	-	-	2,00	8,70	-	-	-
Max.	68,25	-	0,20	0,35	-	2,50	-	-	-	-

**With XRF Spectrometer

The above figures are typical, average values derived from numerous measurements. This is not a specification

kaltun

Aydin- Mugla Karayolu 35. Km. 09500 Cine/Aydin-TURKIYE

Phone : +90 256 729 16 00

Fax : +90 256 729 16 15

Web : <http://www.kaltun.com>

e-mail : kaltun@kaltun.com.tr

Doc.No : Cera007
Issued Date : 13.05.2014
Revision : 2